

MadFlex Mass impact

	UNITÀ	VALORE TIPICO	TEST
Thickness	mm	5	
Areal weight	kg/m ²	1,4	
Tensile strength	kN/m	500	ASTM D3039/D3039M
Failure bending moment	N·m/m	180	ASTM D7250/D7250M
Bending stiffness "rigid side"	N·m ² /m	45	ASTM D7250/D7250M
Bending stiffness "flexible side"	N·m ² /m	0,31	ASTM D7250/D7250M
Flatwise compressive strength	MPa	1,6	ASTM C365/C365M
Heat transfer coefficient	W/ m ² °K	7,2	DIN52612

